CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC- 5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Date: 11/08/2018

Lab ID	:	**CP-2018-08-06-09**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and construction of CC road at Urdu school opp road and cross roads at Dasarahalli in Ward No.15
Agency	:	Nandi Enterprises (Pro. P Vijaya Babu) No 1504 4th 'C' Main, 2nd Stage WOC Road, Bangalore-560086
Customer's Reference	:	EE/DD/WO/13/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-08-18
Sample ID No	:	2018-08-06-09 /01
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	149.40 X 151.89 X 150.56	22692	8.027	565.0	24.9	25.1
2	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	149.33 X 151.48 X 149.58	22621	8.118	579.1	25.6	
3	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	150.88 X 149.26 X 150.94	22520	8.383	558.5	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC- 9548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : CP-2018-08-06-09

Date: 01/09/2018

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Providing and construction of CC road at Urdu school opp road and cross roads at Dasarahalli in Ward No.15

Agency : Nandi Enterprises (Pro. P Vijaya Babu) No 1504 4th 'C' Main, 2nd Stage WOC Road, Bangalore-560086

Customer's Reference : EE/DD/WO/13/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 06-08-18

Sample ID No : 2018-08-06-09 /02

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	151.37 X 149.39 X 149.45	22613	8.353	750.7	33.2	32.8
2	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	149.24 X 150.29 X 149.94	22429	8.442	726.7	32.4	
3	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	150.75 X 150.19 X 149.83	22640	8.177	744.9	32.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರ
ಬಿ.ಡಾಸರಹಳ್ಳಿ ಉಪ
ಬಾಗಲಗುಂಟೆ, ಬೆಂಗಳೂರು

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5648

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-06-09** **Date: 11/08/2018**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Providing and construction of CC road at Urdu school opp road and cross roads at Dasarahalli in Ward No.15

Agency : Nandi Enterprises (Pro. P Vijaya Babu) No 1504 4th 'C' Main, 2nd Stage WOC Road, Bangalore-560086

Customer's Reference : EE/DD/WO/13/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 06-08-18

Sample ID No : 2018-08-06-09 /01

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	151.55 X 151.99 X 149.51	23035	8.381	578.2	25.1	25.4
2	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	150.09 X 149.20 X 149.77	22395	8.528	582.3	26.0	
3	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	150.60 X 149.10 X 151.94	22455	7.965	565.9	25.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No. TC- 1548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-08-06-09** **Date: 01/09/2018**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and construction of CC road at Urdu school opp road and cross roads at Dasarahalli in Ward No.15
Agency	:	Nandi Enterprises (Pro. P Vijaya Babu) No 1504 4th 'C' Main, 2nd Stage WOC Road, Bangalore-560086
Customer's Reference	:	EE/DD/WO/13/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-08-18
Sample ID No	:	2018-08-06-09 /02
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	150.63 X 149.49 X 151.04	22517	8.152	740.8	32.9	32.6
2	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	151.08 X 151.11 X 151.21	22831	8.137	742.0	32.5	
3	Cement Concrete Pavement	M30	04/08/2018	01/09/2018	150.20 X 149.39 X 151.31	22439	8.136	727.0	32.4	

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬೆಂ.ನಗರ
ಬೆಂಗಳೂರು

****End of Report****

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE
Sig.....
Date.....

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-08-06-09** **Date: 11/08/2018**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and construction of CC road at Urdu school opp road and cross roads at Dasarahalli in Ward No.15
Agency	:	Nandi Enterprises (Pro. P Vijaya Babu) No 1504 4th 'C' Main, 2nd Stage WOC Road, Bangalore-560086
Customer's Reference	:	EE/DD/WO/13/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-08-18
Sample ID No	:	2018-08-06-09 /01
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	151.45 X 149.70 X 151.86	22672	8.308	587.2	25.9	25.1
2	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	149.45 X 150.21 X 149.38	22448	7.966	556.7	24.8	
3	Cement Concrete Pavement	M30	04/08/2018	11/08/2018	149.43 X 149.42 X 149.89	22327	8.339	547.0	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT |

Scanned by CamScanner